


EVERBLAST SYSTEMS SDN BHD

PARTICLE SIZE ANALYSIS REPORT

| Mesh | MM | Retained % | |
|------|-------|------------|---------|
| | | Guaranteed | Typical |
| 70 | 0.212 | 1 ~ 3 | 2.30 |
| 80 | 0.180 | 10 ~ 20 | 18.70 |
| 100 | 0.150 | 58 ~ 75 | 60.25 |
| 120 | 0.125 | 10 ~ 20 | 12.80 |
| 140 | 0.106 | 5 ~ 8 | 5.75 |
| -140 | 0.090 | 0 ~ 1 | 0.2 |



rr

MINERALOGICAL REPORT

| Minerals | Guaranteed | Typical |
|----------|-------------|---------|
| Garnet | Min 97.00 % | 97.50 % |
| Ilmenite | Max 01.50 % | 01.20 % |
| Others | Max 01.50 % | 01.30 % |

PHYSICAL PARAMETERS

| Parameters | Guaranteed | TYPICAL |
|------------------|-----------------------------|------------------------|
| Conductivity | Max 18.0 mS/m | 15.72 mS/m |
| Chloride | Max 25 ppm | 19.81 ppm |
| Specific gravity | 4.1 ~ 4.3 | 4.10 |
| Bulk density | 2.3 ~ 2.7 g/cm ³ | 2.49 g/cm ³ |
| Hardness | Avg 7 moh scale | 7.5 moh scale |
| Suspended Solid | Max 1600 mg/l | 1450 mg/l |
| Moisture | Max 0.25 % | 0.23 % |
| Toxic substances | None | None |

CHEMICAL CONTENT

| Elements | Guaranteed | TYPICAL |
|--------------------------------|---------------|---------|
| SiO ₂ | 35.0 ~ 38.0 % | 35.44 % |
| Al ₂ O ₃ | 19.0 ~ 22.0 % | 20.46 % |
| Fe ₂ O ₃ | 30 ~ 35.0 % | 30.41 % |
| MgO | 6.0 ~ 8.0 % | 6.72 % |
| CaO | 1.0 ~ 2.0 % | 1.26 % |
| TiO ₂ | 1.0 ~ 3.0 % | 3.14 % |

*Garnet being a natural product, its analysis is expected to vary periodically and between deposits